

Chartwell C-515.71/ 1.5H

TECHNICAL DATA

ADHESION PROMOTERS

GENERAL DESCRIPTION: A high active matter amino functional metal organic adhesion promoter synthesized with a stabilized neutralized metal complex. The product is supplied as a solution in propylene glycol.

PHYSICAL PROPERTIES:

Physical form	Clear liquid
Color	pale yellow
Metal content (Total %)	7.3 - 7.9
Complexed organics	19.6 - 20.4
Specific gravity (g/ml)	1.31
pH (1% soln)	7.7
Active matter (wt %)	51.0
Solvent	propylene glycol
Organofunctionality	amino
Neutralizing agent:	caustic

APPLICATION:

Coatings, Adhesives & Inks: Will improve adhesion to all metals with accompanying improved salt fog resistance, reduction of creep at the scribe, and reduced blistering; AND improved adhesion to plastics, ceramics, concrete and wood. In WB Exterior primers and deck stains, will eliminate peeling on wood substrate.

- **Water-Borne Coatings:** For acrylic, styrenated acrylic, PUD and alkyd coatings having pH 7-11. Use level 0.35 - 1.4 wt per cent on polymer solids*.
- **2K Epoxy and 2K Urethane:** Always add to hardener (epoxies) or polyol (urethanes). Use level 0.35 - 1.4 wt. per cent on polymer solids*.
- **Urethane modified nitrocellulose:** Add with Cowles-type mixing for 10 minutes. Use level 0.35 - 1.4 wt per cent based upon binder solids.

PROCEDURE:

1. **Water-Borne:** Post add at **0.35 - 1.4 wt per cent on polymer solids***. Mix with conventional paddle-type mixer.
2. **2K Epoxy and 2K Urethane:** Optimum performance is achieved when added to the hardener (epoxies) or polyol (urethanes). **Product must be high shear mixed with a Cowles type mixer. Milling alone is not sufficient. Use Level 0.35 - 1.4 wt per cent on polymer solids*.**

**Plus organic pigment weight if applicable*

Chartwell C-515.71/ 1.5H Data Sheet Rev. 9/07



Chartwell International, Inc.
100 John Dietsch Blvd. Attleboro Falls, MA 02763/ USA

For further information, visit our website: www.chartwellintl.com
Or contact us by: Telephone (508) 695-1690 or Fax (508) 699-6693