

GENERAL DESCRIPTION: An increased reactivity hybrid carboxy/ hydroxy functional metal organic adhesion promoter synthesized with a stabilized neutralized metal complex. The product is supplied as a solution in propylene glycol.

PHYSICAL PROPERTIES:

Physical form	Clear liquid
Color	pale yellow
Metal content (Total %)	7.3 - 7.9
Complexed organics	24.4 - 25.2
Specific gravity (g/ml)	1.24
pH (1% soln)	6.1
Active matter (wt %)	33.5
Solvent	propylene glycol
Organofunctionality	carboxy/ hydroxy
Neutralizing agent:	caustic

APPLICATION:

(1) Coatings/ Adhesives: Recommended for enhancing adhesion of high solids solvent-borne (or 100% solids) polyester, alkyd, acrylic, epoxy, and urethane coatings/ adhesives to:

- All metals, improve salt fog resistance, reduce creep at the scribe, and reduce blistering
- Many plastics, including ABS and treated PP/ PE
- Also, improved adhesion to many plastics, concrete, rubber, wood and ceramics

(2) Pigment Dispersion: Recommended for dispersion of difficult to disperse pigments, i.e. phthalo blue/ green, carbon black, etc. Also for all inorganic pigments, conductive pigments, and mineral fillers.

PROCEDURE: HIGH SHEAR MIXING NECESSARY IN ALL SOLVENT-BORNE SYSTEMS

1. Coatings: 0.35 - 1.4 wt per cent based upon combined polymer solids + anti-corrosive pigments + inorganic pigments. Optimum performance is achieved when added directly to the grind stage resin and high shear mixed for 15 mins before adding other components. **Must be high shear mixed with a Cowles type mixer. Milling alone is not sufficient.**

2. Adhesives: 0.35 - 1.4 phr. High shear mix with Cowles or similar mixer.

3. Pigment Dispersion: 2.2 wt per cent based upon organic (phthalo, carbon black, etc.) plus 1.1 per cent based upon inorganic pigment weight. High shear mix with Cowles or similar mixer.

